



Part Number: **HF-134060-2**
 Revision 20160816 - Generated 2016-Aug-16



OD	(nom. - bare core) (max. - after coating)	33.02 mm 33.83 mm	1.300 in 1.332 in
ID	(nom. - bare core) (min. - after coating)	19.94 mm 19.30 mm	0.785 in 0.760 in
Ht	(nom. - bare core) (max. - after coating)	18.00 mm 19.00 mm	0.709 in 0.748 in
Mass	(approximate)	62 grams	
Magnetic Dimensions	A _e - Eff. Mag. Cross Section	1.10 cm ²	
	L _e - Eff. Mag. Path Length	8.15 cm	
	V _e - Eff. Core Volume	8.98 cm ³	
	WA - Min. Eff. Window Area	2.93 cm ²	
	sa - Surface Area	49.1 cm ²	
	mlt - mean length per turn	6.22 cm	
Inductance	μ _i (reference)	60	
	A _L value (nominal)	102 nH/N ²	
	Test Winding	N=70, #22 AWG	
	Frequency	10 kHz	
	Voltage on Agilent 4284A	0.34 V	
AL tolerance	±8%		
Core Loss	$\text{Core Loss (mW/cm}^3\text{)} = \frac{f}{\frac{a}{B_{pk}^3} + \frac{b}{B_{pk}^{2.3}} + \frac{c}{B_{pk}^{1.65}}} + d \cdot B_{pk}^2 \cdot f^2$		
	where B _{pk} expressed in gauss, f expressed in hertz, and: a=8.579E+09, b=7.879E+08, c=1.650E+06, d=1.019E-13		
	B _{pk}	1000 G	
	frequency	50 kHz	
	Core Loss (nominal)	651 mW/cm ³	
Core Loss (maximum)	748 mW/cm ³		
DC Saturation	$\% \mu_i = \frac{1}{a + b \cdot H^c} + d$		
	where H expressed in oersteds, and: a=1.000E-02, b=7.648E-07, c=1.888, d=0.000		
	H _{DC}	100 Oe	
	Percent Initial Perm.(nom.)	68.6%	
Percent Initial Perm.(min.)	60.8%		
Coating/Pkg	Coating Type:	Blue Epoxy	
	Voltage Breakdown (min.)	1000 Vrms	
	Limit	0.1 mA, 5 s	
	Package Quantity	192 Pcs/Box	

Winding Table	Wire Size	AWG	8	10	12	14	16	18	20	22	24	26	28
		mm	3.150	2.500	2.000	1.600	1.250	1.000	0.800	0.630	0.500	0.400	0.315
	Single Layer	Turns	14	18	22	29	36	46	58	73	91	114	142
		Rdc(Ω)	1.8 m	3.7 m	7.1 m	14.9 m	29.4 m	59.8 m	120.0 m	240.2 m	476.2 m	948.7 m	1.9
Full Winding	Turns	15	24	37	57	88	136	211	326	504	780	1,208	
	Rdc(Ω)	1.9 m	4.9 m	12.0 m	29.3 m	72.0 m	176.9 m	436.5 m	1.1	2.6	6.5	16.0	

