



**Part Number: MP-301014-2**  
Revision 20160816 - Generated 2016-Aug-16



<b>OD</b>	(nom. - bare core)	77.80 mm	3.063 in
	(max. - after coating)	78.94 mm	3.108 in
<b>ID</b>	(nom. - bare core)	49.23 mm	1.938 in
	(min. - after coating)	47.96 mm	1.888 in
<b>Ht</b>	(nom. - bare core)	15.88 mm	0.625 in
	(max. - after coating)	17.15 mm	0.675 in
<b>Mass</b>	(approximate)	260 grams	
<b>Magnetic Dimensions</b>	A <sub>e</sub> - Eff. Mag. Cross Section	2.22 cm <sup>2</sup>	
	L <sub>e</sub> - Eff. Mag. Path Length	19.612 cm	
	V <sub>e</sub> - Eff. Core Volume	43.5 cm <sup>3</sup>	
	WA - Min. Eff. Window Area	18.1 cm <sup>2</sup>	
	sa - Surface Area	193 cm <sup>2</sup>	
	mlt - mean length per turn	8.93 cm	
<b>Inductance</b>	μ <sub>i</sub> (reference)	14	
	A <sub>L</sub> value (nominal)	19.9 nH/N <sup>2</sup>	
	Test Winding	N=120, #18 AWG	
	Frequency	10 kHz	
	Voltage on Agilent 4284A	1.2 V	
AL tolerance	±8%		
<b>Core Loss</b>	Core Loss(mW/cm <sup>3</sup> )= $\frac{f}{\frac{a}{B_{pk}^3} + \frac{b}{B_{pk}^{2.3}} + \frac{c}{B_{pk}^{1.65}}} + d \cdot B_{pk}^2 \cdot f^2$		
	where B <sub>pk</sub> expressed in gauss, f expressed in hertz, and: a=1.914E+09, b=4.349E+08, c=4.331E+06, d=8.850E-14		
	B <sub>pk</sub>	300 G	
	frequency	100 kHz	
	Core Loss (nominal)	157 mW/cm <sup>3</sup>	
Core Loss (maximum)	180 mW/cm <sup>3</sup>		
<b>DC Saturation</b>	%μ <sub>i</sub> = $\frac{1}{a + b \cdot H^c} + d$		
	where H expressed in oersteds, and: a=1.000E-02, b=5.683E-07, c=1.662, d=0.000		
	H <sub>DC</sub>	200 Oe	
	Percent Initial Perm.(nom.)	72.5%	
Percent Initial Perm.(min.)	66.0%		
<b>Coating/Pkg</b>	Coating Type:	Blue Epoxy	
	Voltage Breakdown (min.)	1000 Vrms	
	Limit	0.1 mA, 5 s	
	Package Quantity	36 Pcs/Box	

<b>Winding Table</b>	<b>Wire Size</b>	AWG	8	10	12	14	16	18	20	22	24	26	28
		mm	3.150	2.500	2.000	1.600	1.250	1.000	0.800	0.630	0.500	0.400	0.315
	<b>Single Layer</b>	Turns	38	48	60	75	95	118	148	185	230	287	358
		Rdc(Ω)	7.0 m	14.0 m	27.9 m	55.4 m	111.5 m	220.3 m	439.5 m	873.8 m	1.7	3.4	6.8
<b>Full Winding</b>	Turns	95	146	227	351	543	840	1,300	2,012	3,114	4,820	7,459	
	Rdc(Ω)	17.4 m	42.6 m	105.4 m	259.1 m	637.6 m	1.6	3.9	9.5	23.4	57.6	141.7	

