



Part Number: **MP-521160-2**
 Revision 20160816 - Generated 2016-Aug-16



OD	(nom. - bare core)	132.54 mm	5.218 in
	(max. - after coating)	134.21 mm	5.284 in
ID	(nom. - bare core)	78.59 mm	3.094 in
	(min. - after coating)	77.04 mm	3.033 in
Ht	(nom. - bare core)	25.40 mm	1.000 in
	(max. - after coating)	26.80 mm	1.055 in
Mass	(approximate)	1,720 grams	
Magnetic Dimensions	A _e - Eff. Mag. Cross Section	6.71 cm ²	
	L _e - Eff. Mag. Path Length	32.429 cm	
	V _e - Eff. Core Volume	218 cm ³	
	WA - Min. Eff. Window Area	46.6 cm ²	
	sa - Surface Area	540 cm ²	
	mlt - mean length per turn	14.9 cm	
Inductance	μ _i (reference)	160	
	A _L value (nominal)	416 nH/N ²	
	Test Winding	N=200, #18 AWG	
	Frequency	10 kHz	
	Voltage on Agilent 4284A	6.0 V	
AL tolerance	±8%		
Core Loss	$\text{Core Loss (mW/cm}^3\text{)} = \frac{f}{\frac{a}{B_{pk}^3} + \frac{b}{B_{pk}^{2.3}} + \frac{c}{B_{pk}^{1.65}}} + d \cdot B_{pk}^2 \cdot f^2$		
	where B _{pk} expressed in gauss, f expressed in hertz, and: a=3.167E+10, b=1.206E+09, c=9.656E+06, d=5.636E-14		
	B _{pk}	1000 G	
	frequency	50 kHz	
	Core Loss (nominal)	312 mW/cm ³	
Core Loss (maximum)	359 mW/cm ³		
DC Saturation	$\% \mu_i = \frac{1}{a + b \cdot H^c} + d$		
	where H expressed in oersteds, and: a=1.000E-02, b=1.123E-05, c=1.935, d=0.000		
	H _{DC}	40 Oe	
	Percent Initial Perm (nom.)	41.4%	
Percent Initial Perm (min.)	33.2%		
Coating/Pkg	Coating Type:	Blue Epoxy	
	Voltage Breakdown (min.)	1000 Vrms	
	Limit	0.1 mA, 5 s	
	Package Quantity	4 Pcs/Box	

Winding Table	Wire Size	AWG	8	10	12	14	16	18	20	22	24	26	28
		mm	3.150	2.500	2.000	1.600	1.250	1.000	0.800	0.630	0.500	0.400	0.315
	Single Layer	Turns	62	78	98	123	154	192	239	298	372	463	577
		Rdc(Ω)	19.0 m	38.1 m	76.1 m	151.9 m	302.4 m	599.6 m	1.2	2.4	4.7	9.3	18.3
Full Winding	Turns	244	378	584	905	1,400	2,167	3,354	5,191	8,035	12,436	19,248	
	Rdc(Ω)	74.9 m	184.5 m	453.4 m	1.1	2.7	6.8	16.7	41.0	100.9	248.5	611.6	

