




Part Number: **SH-065026-2**

Revision 20170403 - Generated 2017-Apr-03



OD	(nom. - bare core) (max. - after coating)	16.64 mm 17.40 mm	0.655 in 0.685 in
ID	(nom. - bare core) (min. - after coating)	10.16 mm 9.53 mm	0.400 in 0.375 in
Ht	(nom. - bare core) (max. - after coating)	6.35 mm 7.11 mm	0.250 in 0.280 in
Mass	(approximate)	4.1 grams	
Magnetic Dimensions	A_e - Eff. Mag. Cross Section L_e - Eff. Mag. Path Length V_e - Eff. Core Volume WA - Min. Eff. Window Area sa - Surface Area mlt - mean length per turn	0.192 cm ² 4.11 cm 0.789 cm ³ 0.713 cm ² 11.2 cm ² 2.69 cm	
Inductance	μ_i (reference) A_L value (nominal) Test Winding Frequency Voltage on Agilent 4284A AL tolerance	26 15 nH/N ² N=70, #28 AWG 10 kHz 0.060 V ±8%	
Core Loss	Core Loss (mW/cm ³) = $\frac{f}{\frac{a}{B_{pk}^3} + \frac{b}{B_{pk}^{2.3}} + \frac{c}{B_{pk}^{1.65}}} + d \cdot B_{pk}^2 \cdot f^2$ where B_{pk} expressed in gauss, f expressed in hertz, and: $a=1.000E+06$, $b=3.287E+08$, $c=5.779E+06$, $d=1.240E-14$ B_{pk} frequency Core Loss (nominal) Core Loss (maximum)	500 G 100 kHz 277 mW/cm ³ 318 mW/cm ³	
DC Saturation	$\% \mu_i = \frac{1}{a + b \cdot H^c} + d$ where H expressed in oersteds, and: $a=1.000E-02$, $b=1.042E-06$, $c=1.701$, $d=0.000$ H_{DC} Percent Initial Perm.(nom.) Percent Initial Perm.(min.)	200 Oe 53.9% 46.1%	
Coating/Pkg	Coating Type: Voltage Breakdown (min.) Limit Package Quantity	Blue Epoxy 1000 Vrms 0.1 mA, 5 s 2,880 Pcs/Box	
Winding Table	Wire Size	AWG	12 14 16 18 20 22 24 26 28 30 32
		mm	2.000 1.600 1.250 1.000 0.800 0.630 0.500 0.400 0.315 0.250 0.200
	Single Layer	Turns	10 13 17 21 27 34 44 55 69 86 108
		Rdc(Ω)	1.4 m 2.9 m 6.0 m 11.8 m 24.1 m 48.3 m 99.4 m 197.7 m 394.4 m 781.8 m 1.6
Full Winding	Turns	9 14 21 33 51 79 123 190 295 456 706	
	Rdc(Ω)	1.3 m 3.1 m 7.4 m 18.5 m 45.6 m 112.3 m 278.0 m 682.9 m 1.7 4.1 10.2	

