




Part Number: **E187-40**

Revision 20160713 - Generated 2016-Aug-15



A	47.37 ± 0.38 mm	1.865 ± 0.015 in
B	19.71 ± 0.20 mm	0.776 ± 0.008 in
C	15.75 ± 0.25 mm	0.620 ± 0.010 in
D	12.09 mm (nom.)	0.476 in (nom.)
E	31.75 mm (nom.)	1.250 in (nom.)
F	15.75 ± 0.18 mm	0.620 ± 0.007 in
Mass	(approximate)	80 grams/half
Magnetic Dimensions	A _e - Eff. Mag. Cross Section	2.48 cm ²
	L _e - Eff. Mag. Path Length	9.53 cm
	V _e - Eff. Core Volume	23.3 cm ³
	WA - Min. Eff. Window Area	1.91 cm ²
	sa - Surface Area	73.6 cm ²
	mlt - mean length per turn	9.50 cm
Inductance	μ _i (reference)	60
	A _L value (nominal)	240 nH/N ²
	Test Winding	N=100, #20 AWG
	Frequency	10 kHz
	Voltage on Agilent 4284A	1.1 V
A _L tolerance	±10%	
Core Loss	$\text{Core Loss (mW/cm}^3\text{)} = \frac{f}{\frac{a}{B_{pk}^3} + \frac{b}{B_{pk}^{2.3}} + \frac{c}{B_{pk}^{1.65}}} + d \cdot B_{pk}^2 \cdot f^2$	
	where B _{pk} expressed in gauss, f expressed in hertz, and: a=1.10E+09, b=3.30E+07, c=2.50E+06, d=3.10E-13	
	B _{pk}	140 G
	frequency	100 kHz
	Core Loss (nominal)	127 mW/cm ³
Core Loss (maximum)	146 mW/cm ³	
DC Saturation	$\% \mu_i = \frac{1}{a + b \cdot H^c} + d$	
	where H expressed in oersteds, and: a=1.00E-02, b=8.93E-06, c=1.61, d=0.00	
	H _{DC}	50 Oe
	Percent Initial Perm(nom.)	67.0%
Percent Initial Perm(min.)	60.2%	
Coating/Pkg	Coating Type:	None, Green/Yellow Stripes
	Voltage Breakdown (min.)	N/A
	Limit	N/A
	Package Quantity	240 Halves/Box

Winding Table	Wire Size	AWG	10	12	14	16	18	20	22	24	26	28	30
		mm	2.500	2.000	1.600	1.250	1.000	0.800	0.630	0.500	0.400	0.315	0.250
	Full Winding	Turns	16	25	38	59	92	142	219	340	526	814	1,259
		Rdc(Ω)	5.0 m	12.4 m	29.9 m	73.7 m	182.8 m	448.8 m	1.1	2.7	6.7	16.5	40.5

