








**Part Number:** EQFS-265190053-060

Revision 20190529 - Generated 2019-May-29



<b>A</b>	26.5 ± 0.30 mm	1.043 ± 0.012 in
<b>B</b>	19 ± 0.20 mm	0.748 ± 0.008 in
<b>C</b>	5.3 ± 0.20 mm	0.209 ± 0.008 in
<b>D</b>	1.7 mm (min.)	0.067 in (min.)
<b>E</b>	12 ± 0.20 mm	0.472 ± 0.008 in
<b>F</b>	22.3 mm (min.)	0.878 in (min.)
<b>Mass</b>	(approximate)	13 grams/half
<b>Magnetic Dimensions</b>	A <sub>e</sub> - Eff. Mag. Cross Section	1.20 cm <sup>2</sup>
	L <sub>e</sub> - Eff. Mag. Path Length	3.55 cm
	V <sub>e</sub> - Eff. Core Volume	4.25 cm <sup>3</sup>
	WA - Min. Eff. Window Area	0.172 cm <sup>2</sup>
	sa - Surface Area	19.6 cm <sup>2</sup>
	mlt - mean length per turn	5.39 cm
<b>Inductance</b>	μ <sub>i</sub> (reference)	60
	A <sub>L</sub> value (nominal)	254 nH/N <sup>2</sup>
	Test Winding	N=8, #26 AWG
	Frequency	10 kHz
	Voltage on Agilent 4284A	0.043 V
	A <sub>L</sub> tolerance	±12%
<b>Core Loss</b>	$\text{Core Loss (mW/cm}^3\text{)} = \frac{f}{\frac{a}{B_{pk}^3} + \frac{b}{B_{pk}^{2.3}} + \frac{c}{B_{pk}^{1.65}}} + d \cdot B_{pk}^2 \cdot f^2$	
	where B <sub>pk</sub> expressed in gauss, f expressed in hertz, and: a=1.00E+06, b=6.14E+08, c=6.14E+04, d=2.67E-14	
	B <sub>pk</sub>	1000 G
	frequency	50 kHz
	Core Loss (nominal)	708 mW/cm <sup>3</sup>
Core Loss (maximum)	814 mW/cm <sup>3</sup>	
<b>DC Saturation</b>	$\% \mu_i = \frac{1}{a + b \cdot H^c} + d$	
	where H expressed in oersteds, and: a=0.01, b=1.71E-06, c=1.66, d=0.00	
	H <sub>DC</sub>	150 Oe
	Percent Initial Perm(nom.)	58.3%
Percent Initial Perm(min.)	50.8%	
<b>Coating/Pkg</b>	Coating Type:	None
	Voltage Breakdown (min.)	N/A
	Limit	N/A
	Package Quantity	1,120 Halves/Box



<b>Winding Table</b>	<b>Wire Size</b>	AWG	22	24	26	28	30	32	34	36	38	40	42
		mm	0.630	0.500	0.400	0.315	0.250	0.200	0.160	0.125	0.100	0.080	0.063
	<b>Full Winding</b>	Turns	20	30	47	73	113	175	271	419	648	1,004	1,553
		Rdc(Ω)	57.0 m	136.0 m	338.9 m	837.2 m	2.1	5.1	12.5	30.7	75.6	186.3	458.3

**Handling and Storage:** Cores should be stored in the original unopened packaging between -10°C and +50°C and less than 60% relative humidity. After the original packaging is opened, the cores should be stored between -8°C and +25°C less than 30% relative humidity. Gloves should be used when handling uncoated cores. The cores should also be sheltered from rain, moisture, salt water, salt air, plasters, ashes, sulfur, sulfur dioxide, ammonia sulfates, soils, acids, metals shavings, and solvents.

**Operating Temperature:** Cores can be used continuously at operating temperatures between -60°C and +200°C.

RoHS 2.0, REACH and ISO (TS16949, ISO 9001, ISO 14001) compliant. Statements available for download at [www.micrometalsapc.com](http://www.micrometalsapc.com).

Micrometals Alloy Powder Cores, A Division of Micrometals, Inc. - 5615 E. La Palma Ave., Anaheim, California 92807 USA

Ph: +1-714-970-9400, Toll Free in USA: +1-800-356-5977, Asia Pacific Sales: +852 3106 3736

[www.MicrometalsAPC.com](http://www.MicrometalsAPC.com)