MICROMETALS™
POWDER CORE SOLUTIONS

Part Number:	EQMS-500320250-060

Revision 20190529 - Generated 2019-May-29



A	50 ± 0.61 mm	1.969 ± 0.024 in
B	32 ± 0.41 mm	1.260 ± 0.016 in
C	25 ± 0.41 mm	0.984 ± 0.016 in
D	19.1 mm (min.)	0.752 in (min.)
E	20 ± 0.30 mm	0.787 ± 0.012 in
F	43.5 mm (min.)	1.713 in (min.)
Mass	(approximate)	110 grams/half
Magnetic Dimensions	A_e - Eff. Mag. Cross Section	3.14 cm²
	L_e - Eff. Mag. Path Length	13.34 cm
	V_e - Eff. Core Volume	41.9 cm³
	WA - Min. Eff. Window Area	4.43 cm²
	sa - Surface Area	110 cm²
	mlt - mean length per turn	9.97 cm
Inductance	μ_i(reference)	60
	A_L value (nominal)	178 nH/N²
	Test Winding	N=30, #18 AWG
	Frequency	10 kHz
	Voltage on Agilent 4284A	0.42 V
	A_L tolerance	±12%
Core Loss	Core Loss(mW/cm³)= $\frac{f}{\frac{a}{Bpk^{3}}+\frac{b}{Bpk^{2.3}}+\frac{c}{Bpk^{1.65}}}+d\cdot Bpk^{2}\cdot f^{2}$	
	where B_{pk} expressed in gauss, f expressed in hertz, and:	
	a=1.00E+06, b=7.12E+08, c=7.40E+06, d=1.30E-14	
	B_{pk}	1000 G
	frequency	50 kHz
	Core Loss (nominal)	322 mW/cm³
	Core Loss (maximum)	370 mW/cm³
DC Saturation	$\%\mu_i = \frac{1}{a + b\cdot H^{c}} + d$	
	where H expressed in oersteds, and:	
	a=0.01, b=6.47E-06, c=1.59, d=0.00	
	H_{DC}	100 Oe
	Percent Initial Perm(nom.)	50.5%
	Percent Initial Perm(min.)	43.3%
Coating/Pkg	Coating Type:	None
	Voltage Breakdown (min.)	N/A
	Limit	N/A
	Package Quantity	72 Halves/Box









Winding Table													
Wire Size	AWG	8	10	12	14	16	18	20	22	24	26	28	
	mm	3.150	2.500	2.000	1.600	1.250	1.000	0.800	0.630	0.500	0.400	0.315	
Full Winding	Turns	24	37	57	89	137	212	328	508	787	1,217	1,884	
	Rdc(Ω)	4.9 m	12.1 m	29.6 m	73.4 m	179.8 m	442.4 m	1.1	2.7	6.6	16.2	40.0	

Handling and Storage: Cores should be stored in the original unopened packaging between -10°C and +50°C and less than 60% relative humidity. After the original packaging is opened, the cores should be stored between -8°C and +25°C less than 30% relative humidity. Gloves should be used when handling uncoated cores. The cores should also be sheltered from rain, moisture, salt water, salt air, plasters, ashes, sulfur, sulfur dioxide, ammonia sulfates, soils, acids, metals shavings, and solvents.

Operating Temperature: Cores can be used continuously at operating temperatures between -60°C and +200°C.

RoHS 2.0, REACH and ISO (TS16949, ISO 9001, ISO 14001) compliant. Statements available for download at www.micrometalsapc.com.

Micrometals Alloy Powder Cores, A Division of Micrometals, Inc. - 5615 E. La Palma Ave., Anaheim, California 92807 USA
Ph: +1-714-970-9400, Toll Free in USA: +1-800-356-5977, Asia Pacific Sales: +852 3106 3736
www.MicrometalsAPC.com