



Part Number: **FS-106026-2**

Revision 20190529 - Generated 2019-May-29



(If coated, Max./Min. includes coating)

| | | | |
|----------------------------|--|------------------------|----------------------|
| OD | (nom. - bare core) (max.) | 26.92 mm 27.69 mm | 1.060 in 1.090 in |
| ID | (nom. - bare core) (min.) | 14.73 mm 14.10 mm | 0.580 in 0.555 in |
| HT | (nom. - bare core) (max.) | 11.18 mm 11.99 mm | 0.440 in 0.472 in |
| Mass | (approximate) | 26 grams | |
| Magnetic Dimensions | A _e - Eff. Mag. Cross Section | 0.654 cm ² | |
| | L _e - Eff. Mag. Path Length | 6.35 cm | |
| | V _e - Eff. Core Volume | 4.15 cm ³ | |
| | WA - Min. Eff. Window Area | 1.56 cm ² | |
| | sa - Surface Area | 28.8 cm ² | |
| | mlt - mean length per turn | 4.46 cm | |
| Inductance | μ _i (reference) | 26 | |
| | A _L value (nominal) | 32 nH/N ² | |
| | Test Winding | N=80, #26 AWG | |
| | Frequency | 10 kHz | |
| | Voltage on Agilent 4284A | 0.23 V | |
| | AL tolerance | ±8% | |
| Core Loss | $\text{Core Loss (mW/cm}^3\text{)} = \frac{f}{\frac{a}{B_{pk}^3} + \frac{b}{B_{pk}^{2.3}} + \frac{c}{B_{pk}^{1.65}}} + d \cdot B_{pk}^2 \cdot f^2$ | | |
| | where B _{pk} expressed in gauss, f expressed in hertz, and: a=1.000E+06, b=1.812E+08, c=3.251E+06, d=6.158E-14 | | |
| | B _{pk} | 300 G | |
| | frequency | 100 kHz | |
| | Core Loss (nominal) | 214 mW/cm ³ | |
| Core Loss (maximum) | 246 mW/cm ³ | | |
| DC Saturation | $\% \mu_i = \frac{1}{a + b \cdot H^c} + d$ | | |
| | where H expressed in oersteds, and: a=1.000E-02, b=9.210E-08, c=1.912, d=0.000 | | |
| | H _{DC} | 200 Oe | |
| | Percent Initial Perm(nom.) | 81.2% | |
| | Percent Initial Perm(min.) | 75.3% | |
| Coating/Pkg | Coating Type: | Blue Epoxy | |
| | Voltage Breakdown (min.) | 1000 Vrms | |
| | Limit | 0.1 mA, 5 s | |
| | Package Quantity | 600 Pcs/Box | |

| | | | | | | | | | | | | | |
|----------------------|---------------------|--------|-------|--------|--------|--------|---------|---------|---------|---------|---------|---------|-------|
| Winding Table | Wire Size | AWG | 10 | 12 | 14 | 16 | 18 | 20 | 22 | 24 | 26 | 28 | 30 |
| | | mm | 2.500 | 2.000 | 1.600 | 1.250 | 1.000 | 0.800 | 0.630 | 0.500 | 0.400 | 0.315 | 0.250 |
| | Single Layer | Turns | 12 | 16 | 20 | 26 | 33 | 41 | 52 | 66 | 82 | 103 | 129 |
| | | Rdc(Ω) | 1.8 m | 3.7 m | 7.4 m | 15.3 m | 30.8 m | 60.9 m | 122.8 m | 247.8 m | 489.7 m | 978.2 m | 1.9 |
| Full Winding | Turns | 13 | 20 | 30 | 47 | 73 | 112 | 174 | 269 | 417 | 645 | 998 | |
| | Rdc(Ω) | 1.9 m | 4.6 m | 11.1 m | 27.6 m | 68.1 m | 166.3 m | 410.8 m | 1.0 | 2.5 | 6.1 | 15.1 | |

