



Part Number: **FS-106060-2**

Revision 20190529 - Generated 2019-May-29



(If coated, Max./Min. includes coating)

OD	(nom. - bare core) (max.)	26.92 mm 27.69 mm	1.060 in 1.090 in
ID	(nom. - bare core) (min.)	14.73 mm 14.10 mm	0.580 in 0.555 in
HT	(nom. - bare core) (max.)	11.18 mm 11.99 mm	0.440 in 0.472 in
Mass	(approximate)	28 grams	
Magnetic Dimensions	A _e - Eff. Mag. Cross Section	0.654 cm ²	
	L _e - Eff. Mag. Path Length	6.35 cm	
	V _e - Eff. Core Volume	4.15 cm ³	
	WA - Min. Eff. Window Area	1.56 cm ²	
	sa - Surface Area	28.8 cm ²	
Inductance	μ _i (reference)	60	
	A _L value (nominal)	75 nH/N ²	
Core Loss	Test Winding	N=80, #26 AWG	
	Frequency	10 kHz	
	Voltage on Agilent 4284A	0.23 V	
	AL tolerance	±8%	
	Core Loss(mW/cm ³)= $\frac{f}{\frac{a}{B_{pk}^3} + \frac{b}{B_{pk}^{2.3}} + \frac{c}{B_{pk}^{1.65}}} + d \cdot B_{pk}^2 \cdot f^2$		
DC Saturation	where B _{pk} expressed in gauss, f expressed in hertz, and: a=1.000E+06, b=3.903E+08, c=3.785E+06, d=5.229E-14		
	B _{pk}	1000 G	
	frequency	50 kHz	
	Core Loss (nominal)	676 mW/cm ³	
Coating/Pkg	Coating Type:	Blue Epoxy	
	Voltage Breakdown (min.)	1000 Vrms	
	Limit	0.1 mA, 5 s	
Winding Table	Package Quantity	600 Pcs/Box	

Winding Table	Wire Size	AWG	10	12	14	16	18	20	22	24	26	28	30
		mm	2.500	2.000	1.600	1.250	1.000	0.800	0.630	0.500	0.400	0.315	0.250
	Single Layer	Turns	12	16	20	26	33	41	52	66	82	103	129
		Rdc(Ω)	1.8 m	3.7 m	7.4 m	15.3 m	30.8 m	60.9 m	122.8 m	247.8 m	489.7 m	978.2 m	1.9
Full Winding	Turns	13	20	30	47	73	112	174	269	417	645	998	
	Rdc(Ω)	1.9 m	4.6 m	11.1 m	27.6 m	68.1 m	166.3 m	410.8 m	1.0	2.5	6.1	15.1	

