



Part Number: FS-132026-2

Revision 20190529 - Generated 2019-May-29



(If coated, Max./Min. includes coating)

OD	(nom. - bare core) (max.)	33.02 mm 33.83 mm	1.300 in 1.332 in
ID	(nom. - bare core) (min.)	19.94 mm 19.30 mm	0.785 in 0.760 in
HT	(nom. - bare core) (max.)	11.18 mm 11.99 mm	0.440 in 0.472 in
Mass	(approximate)	36 grams	
Magnetic Dimensions	A _e - Eff. Mag. Cross Section	0.698 cm ²	
	L _e - Eff. Mag. Path Length	8.15 cm	
	V _e - Eff. Core Volume	5.69 cm ³	
	WA - Min. Eff. Window Area	2.93 cm ²	
	sa - Surface Area	40.6 cm ²	
Inductance	μ _i (reference)	26	
	A _L value (nominal)	28 nH/N ²	
Core Loss	Test Winding	N=70, #22 AWG	
	Frequency	10 kHz	
	Voltage on Agilent 4284A	0.22 V	
	AL tolerance	±8%	
	Core Loss(mW/cm ³)= $\frac{f}{\frac{a}{B_{pk}^3} + \frac{b}{B_{pk}^{2.3}} + \frac{c}{B_{pk}^{1.65}}} + d \cdot B_{pk}^2 \cdot f^2$		
DC Saturation	where B _{pk} expressed in gauss, f expressed in hertz, and: a=1.000E+06, b=1.812E+08, c=3.251E+06, d=6.158E-14		
	B _{pk}	300 G	
	frequency	100 kHz	
	Core Loss (nominal)	214 mW/cm ³	
	Core Loss (maximum)	246 mW/cm ³	
Coating/Pkg	Coating Type:	Blue Epoxy	
	Voltage Breakdown (min.)	1000 Vrms	
	Limit	0.1 mA, 5 s	
	Package Quantity	448 Pcs/Box	

Winding Table	Wire Size	AWG	8	10	12	14	16	18	20	22	24	26	28
		mm	3.150	2.500	2.000	1.600	1.250	1.000	0.800	0.630	0.500	0.400	0.315
	Single Layer	Turns	14	18	22	29	36	46	58	73	91	114	142
		Rdc(Ω)	1.4 m	2.8 m	5.5 m	11.6 m	22.8 m	46.3 m	92.9 m	186.0 m	368.8 m	734.8 m	1.5
Full Winding	Turns	15	24	37	57	88	136	211	326	504	780	1,208	
	Rdc(Ω)	1.5 m	3.8 m	9.3 m	22.7 m	55.7 m	137.0 m	338.1 m	830.8 m	2.0	5.0	12.4	

