Part Number:	HF-132160-2

Revision 20160816 - Generated 2016-Aug-16



OD	(nom. - bare core)	33.02 mm	1.300 in
	(max. - after coating)	33.83 mm	1.332 in
ID	(nom. - bare core)	19.94 mm	0.785 in
	(min. - after coating)	19.30 mm	0.760 in
Ht	(nom. - bare core)	11.18 mm	0.440 in
	(max. - after coating)	11.99 mm	0.472 in
Mass	(approximate)	44 grams	
Magnetic Dimensions	A_e - Eff. Mag. Cross Section	0.698 cm²	
	L_e - Eff. Mag. Path Length	8.15 cm	
	V_e - Eff. Core Volume	5.69 cm³	
	WA - Min. Eff. Window Area	2.93 cm²	
	sa - Surface Area	40.6 cm²	
	mlt - mean length per turn	4.82 cm	
Inductance	μ_i(reference)	160	
	A_L value (nominal)	172 nH/N²	
	Test Winding	N=70, #22 AWG	
	Frequency	10 kHz	
	Voltage on Agilent 4284A	0.22 V	
	AL tolerance	±8%	
Core Loss	Core Loss(mW/cm³)= $\frac{f}{\frac{a}{Bpk^{3}}+\frac{b}{Bpk^{2.3}}+\frac{c}{Bpk^{1.65}}}+d\cdot Bpk^{2}\cdot f^{2}$		
	where B_{pk} expressed in gauss, f expressed in hertz, and: *a=4.299E+10, b=6.671E+08, c=3.114E+06, d=8.003E-14*		
	B_{pk}	1000 G	
	frequency	50 kHz	
	Core Loss (nominal)	509 mW/cm³	
	Core Loss (maximum)	585 mW/cm³	
DC Saturation	$\%\mu_i = \frac{1}{a+b\cdot H^{c}}+d$		
	where H expressed in oersteds, and: *a=1.000E-02, b=1.434E-06, c=2.169, d=0.000*		
	H_{DC}	40 Oe	
	Percent Initial Perm(nom.)	70.0%	
	Percent Initial Perm(min.)	61.1%	
Coating/Pkg	Coating Type:	Blue Epoxy	
	Voltage Breakdown (min.)	1000 Vrms	
	Limit	0.1 mA, 5 s	
	Package Quantity	320 Pcs/Box	









Winding Table													
Wire Size	AWG	8	10	12	14	16	18	20	22	24	26	28
	mm	3.150	2.500	2.000	1.600	1.250	1.000	0.800	0.630	0.500	0.400	0.315
Single Layer	Turns	14	18	22	29	36	46	58	73	91	114	142
	Rdc(Ω)	1.4 m	2.8 m	5.5 m	11.6 m	22.8 m	46.3 m	92.9 m	186.0 m	368.8 m	734.8 m	1.5
Full Winding	Turns	15	24	37	57	88	136	211	326	504	780	1,208
	Rdc(Ω)	1.5 m	3.8 m	9.3 m	22.7 m	55.7 m	137.0 m	338.1 m	830.8 m	2.0	5.0	12.4

Micrometals Alloy Powder Cores, A Division of Micrometals, Inc. - 5615 E. La Palma Ave., Anaheim, California 92807 USA
Ph: +1-714-970-9400, Toll Free in USA: +1-800-356-5977, Asia Pacific Sales: +852 3106 3736
www.MicrometalsAPC.com