




Part Number: **HF-250060-2**
 Revision 20161018 - Generated 2016-Oct-26



OD	(nom. - bare core) (max. - after coating)	63.50 mm 64.77 mm	2.500 in 2.550 in
ID	(nom. - bare core) (min. - after coating)	31.37 mm 30.48 mm	1.235 in 1.200 in
Ht	(nom. - bare core) (max. - after coating)	25.00 mm 25.90 mm	0.984 in 1.020 in
Mass	(approximate)	380 grams	
Magnetic Dimensions	A _e - Eff. Mag. Cross Section	3.89 cm ²	
	L _e - Eff. Mag. Path Length	14.314 cm	
	V _e - Eff. Core Volume	55.8 cm ³	
	WA - Min. Eff. Window Area	7.30 cm ²	
	sa - Surface Area	150 cm ²	
	mlt - mean length per turn	10.1 cm	
	Inductance	μ _i (reference) A _L value (nominal) Test Winding Frequency Voltage on Agilent 4284A AL tolerance	60 206 nH/N ² N=100, #18 AWG 10 kHz 1.7 V ±8%
Core Loss	Core Loss(mW/cm ³): $\frac{f}{\frac{a}{Bpk^3} + \frac{b}{Bpk^{2.3}} + \frac{c}{Bpk^{1.65}}} + d \cdot Bpk^2 \cdot f^2$ where B _{pk} expressed in gauss, f expressed in hertz, and: a=8.579E+09, b=7.879E+08, c=1.650E+06, d=1.019E-13		
	B _{pk}	1000 G	
	frequency	50 kHz	
	Core Loss (nominal)	651 mW/cm ³	
	Core Loss (maximum)	748 mW/cm ³	
DC Saturation	$\% \mu_i = \frac{1}{a + b \cdot H^c} + d$ where H expressed in oersteds, and: a=1.000E-02, b=7.648E-07, c=1.888, d=0.000		
	H _{DC}	100 Oe	
	Percent Initial Perm(nom.)	68.6%	
	Percent Initial Perm(min.)	60.8%	
Coating/Pkg	Coating Type:	Blue Epoxy	
	Voltage Breakdown (min.)	1000 Vrms	
	Limit	0.1 mA, 5 s	
	Package Quantity	27 Pcs/Box	

Winding Table	Wire Size	AWG	8	10	12	14	16	18	20	22	24	26	28
		mm	3.150	2.500	2.000	1.600	1.250	1.000	0.800	0.630	0.500	0.400	0.315
	Single Layer	Turns	23	29	37	47	59	74	93	116	145	182	227
		Rdc(Ω)	4.8 m	9.6 m	19.5 m	39.4 m	78.6 m	156.9 m	313.5 m	622.0 m	1.2	2.5	4.9
Full Winding	Turns	38	59	91	142	219	339	525	813	1,258	1,947	3,013	
	Rdc(Ω)	7.9 m	19.6 m	48.0 m	119.0 m	291.9 m	718.6 m	1.8	4.4	10.7	26.4	65.0	

