




**Part Number: SH-184060-2**

Revision 20170403 - Generated 2017-Apr-03



<b>OD</b>	(nom. - bare core) (max. - after coating)	46.74 mm 47.63 mm	1.840 in 1.875 in										
<b>ID</b>	(nom. - bare core) (min. - after coating)	24.13 mm 23.32 mm	0.950 in 0.918 in										
<b>Ht</b>	(nom. - bare core) (max. - after coating)	18.03 mm 18.92 mm	0.710 in 0.745 in										
<b>Mass</b>	(approximate)	120 grams											
<b>Magnetic Dimensions</b>	A <sub>e</sub> - Eff. Mag. Cross Section	1.99 cm <sup>2</sup>											
	L <sub>e</sub> - Eff. Mag. Path Length	10.743 cm											
	V <sub>e</sub> - Eff. Core Volume	21.4 cm <sup>3</sup>											
	WA - Min. Eff. Window Area	4.27 cm <sup>2</sup>											
	sa - Surface Area	81.7 cm <sup>2</sup>											
	mlt - mean length per turn	7.38 cm											
<b>Inductance</b>	μ <sub>i</sub> (reference)	60											
	A <sub>L</sub> value (nominal)	135 nH/N <sup>2</sup>											
	Test Winding	N=70, #20 AWG											
	Frequency	10 kHz											
	Voltage on Agilent 4284A	0.62 V											
	AL tolerance	±8%											
<b>Core Loss</b>	$\text{Core Loss (mW/cm}^3\text{)} = \frac{f}{\frac{a}{B_{pk}^3} + \frac{b}{B_{pk}^{2.3}} + \frac{c}{B_{pk}^{1.65}}} + d \cdot B_{pk}^2 \cdot f^2$												
	where B <sub>pk</sub> expressed in gauss, f expressed in hertz, and: a=1.000E+06, b=8.801E+08, c=5.421E+06, d=1.033E-14												
	B <sub>pk</sub>	1000 G											
	frequency	50 kHz											
	Core Loss (nominal)	317 mW/cm <sup>3</sup>											
Core Loss (maximum)	365 mW/cm <sup>3</sup>												
<b>DC Saturation</b>	$\% \mu_i = \frac{1}{a + b \cdot H^c} + d$												
	where H expressed in oersteds, and: a=1.000E-02, b=7.724E-06, c=1.612, d=0.000												
	H <sub>0c</sub>	100 Oe											
	Percent Initial Perm.(nom.)	43.6%											
Percent Initial Perm.(min.)	36.5%												
<b>Coating/Pkg</b>	Coating Type:	Blue Epoxy											
	Voltage Breakdown (min.)	1000 Vrms											
	Limit	0.1 mA, 5 s											
	Package Quantity	100 Pcs/Box											
<b>Winding Table</b>	<b>Wire Size</b>	AWG	8	10	12	14	16	18	20	22	24	26	28
		mm	3.150	2.500	2.000	1.600	1.250	1.000	0.800	0.630	0.500	0.400	0.315
	<b>Single Layer</b>	Turns	17	22	28	35	45	56	70	88	111	138	173
		Rdc(Ω)	2.6 m	5.3 m	10.7 m	21.4 m	43.7 m	86.5 m	171.9 m	343.7 m	689.5 m	1.4	2.7
<b>Full Winding</b>	Turns	22	35	54	83	128	199	307	476	736	1,139	1,764	
	Rdc(Ω)	3.3 m	8.4 m	20.7 m	50.7 m	124.3 m	307.3 m	753.9 m	1.9	4.6	11.3	27.7	

