



TEL (714) 970-9400  
USA (800) 356-5977  
FAX (714) 970-0400

Data Sheet  
Part Number: ST50-267

Description: Composite Iron Powder Toroidal Core

Finished Dimensions: Inches (millimeters) – includes coating

Outside Diameter: 0.525 / 0.495 (13.34 / 12.57)  
Inside Diameter: 0.305 / 0.275 ( 7.75 / 6.99)  
Height: 0.300 / 0.260 ( 7.62 / 6.60)

Magnetic Dimensions:

Magnetic Path Length: 3.19 cm  
Cross Sectional Area: 0.189 cm<sup>2</sup> (Combined)  
Volume: 0.603 cm<sup>3</sup>

Basic Material Characteristics:

Material Type: Ferrite, 33% + Micrometals Mix -52, 67%  
Initial Permeability: 2300 + 75 (reference)  
Temperature Stability: N/A  
Color Code: Green / Green  
Finish: Per UL Card File #E140098 (S)

Inductance Index:

450nH/N<sup>2</sup> +35%, -25%  
Test Winding: 50 turns, AWG-26, single—evenly spaced layer, tightly wound, 1/2" leads  
Test Instrument: HP4274A  
Test Frequency: 10 kHz  
Test Voltage: 0.04V (B ac = 10 gauss)  
Inductance: 1519uH / 843uH

Note: The Ferrite core material is temperature sensitive and the inductance will increase as the temperature increases. Minimize handling of the wound core during test. Maintain part at +25C for testing. A small gap or parting line between the cores is normal and acceptable, not a cause for rejection. The Thermal Aging properties of Micrometals Mix -52 are unique to Micrometals alone and not our competitors. Micrometals color codes are protected by US Patent and trade Mark Law. All other magnetic properties as described in Micrometals Power Conversion Catalog, Issue L, Feb'07. Micrometals Iron Powder Cores comply with the EU Directives 2002/95/EC and 2003/11/EC. Any possible unintentional RoHS trace elements present are less than 100 ppm.