




Part Number: **T10-1**
Revision 20190404 - Generated 2019-Apr-04



OD	(nom. - bare core)	2.46 mm	0.097 in
	(max. - after coating)	2.59 mm	0.102 in
ID	(nom. - bare core)	1.12 mm	0.044 in
	(min. - after coating)	0.99 mm	0.039 in
Ht	(nom. - bare core)	0.76 mm	0.030 in
	(max. - after coating)	0.89 mm	0.035 in
Mass	(approximate)	0.02 grams	
Magnetic Dimensions	A _e - Eff. Mag. Cross Section	0.00450 cm ²	
	L _e - Eff. Mag. Path Length	0.560 cm	
	V _e - Eff. Core Volume	0.00250	
	WA - Min. Eff. Window Area	0.00771 cm ²	
	sa - Surface Area	0.219 cm ²	
	mlt - mean length per turn	0.387 cm	
Inductance	μ _i (reference)	20	
	A _L value (nominal)	3.2 nH/N ²	
	Test Winding	N=25, #40 AWG	
	Frequency	1 MHz	
	Voltage on Agilent 4284A	0.050 V	
	A _L tolerance	±10%	
Core Loss	Core Loss(mW/cm ³)= $\frac{f}{Bpk^3 + \frac{b}{Bpk^{2.3}} + \frac{c}{Bpk^{1.65}}} + d \cdot Bpk^2 \cdot f^2$		
	where B _{pk} expressed in gauss, f expressed in hertz, and: a=1.90E+09, b=2.00E+08, c=9.00E+05, d=4.30E-15		
	Bpk	140 G	
	frequency	100 kHz	
	Core Loss (nominal)	31 mW/cm ³	
	Core Loss (maximum)	36 mW/cm ³	
DC Saturation	$\% \mu_i = \frac{1}{a + b \cdot H^c} + d$		
	where H expressed in oersteds, and: a=1.00E-02, b=1.14E-06, c=1.43, d=0.00		
	H _{DC}	200 Oe	
	Percent Initial Perm(nom.)	82.2%	
	Percent Initial Perm(min.)	78.0%	
Coating/Plg	Coating Type:	Parylene C	
	Voltage Breakdown (min.)	500 Vrms, 60Hz	
	Limit	3 mA, 5 s	
	Package Quantity	250,000 Pcs/Box	

Winding Table	Wire Size	AWG	34	36	38	40	42	44	#N/A	#N/A	#N/A	#N/A	#N/A
		mm	0.160	0.125	0.100	0.080	0.063	0.050	#N/A	#N/A	#N/A	#N/A	#N/A
	Single Layer	Turns	12	15	19	25	32	40	#N/A	#N/A	#N/A	#N/A	#N/A
		Rdc(Ω)	39.8 m	79.1 m	159.4 m	333.5 m	679.0 m	1.3	#N/A	#N/A	#N/A	#N/A	#N/A
Full Winding	Turns	12	18	28	44	68	105	#N/A	#N/A	#N/A	#N/A	#N/A	
	Rdc(Ω)	39.8 m	94.9 m	234.9 m	587.0 m	1.4	3.5	#N/A	#N/A	#N/A	#N/A	#N/A	

