




Part Number: **T12-17**

Revision 20190404 - Generated 2019-Apr-04



OD	(nom. - bare core)	3.18 mm	0.125 in
	(max. - after coating)	3.30 mm	0.130 in
ID	(nom. - bare core)	1.57 mm	0.062 in
	(min. - after coating)	1.45 mm	0.057 in
Ht	(nom. - bare core)	1.27 mm	0.050 in
	(max. - after coating)	1.40 mm	0.055 in
Mass	(approximate)	0.04 grams	
Magnetic Dimensions	A_e - Eff. Mag. Cross Section	0.0100 cm ²	
	L_e - Eff. Mag. Path Length	0.750 cm	
	V_e - Eff. Core Volume	0.00770	
	W_A - Min. Eff. Window Area	0.0165 cm ²	
	s_a - Surface Area	0.395 cm ²	
	mlt - mean length per turn	0.537 cm	
Inductance	μ_i (reference)	4	
	A_L value (nominal)	0.75 nH/N ²	
	Test Winding	N=25, #36 AWG	
	Frequency	1 MHz	
	Voltage on Agilent 4284A	0.11 V	
	A_L tolerance	±5%	
Core Loss & Q	Core Loss(mW/cm ³)= $\frac{f}{B_{pk}^3 + \frac{b}{B_{pk}^{2.3}} + \frac{c}{B_{pk}^{1.65}}} + d \cdot B_{pk}^2 \cdot f^2$		
	where B_{pk} expressed in gauss, f expressed in hertz, and: $a=4.00E+09$, $b=3.00E+08$, $c=2.70E+06$, $d=4.40E-16$		
	Q test winding	N=9, #30 AWG	
	Q frequency	70 MHz	
DC Saturation	$\% \mu_i = \frac{1}{a + b \cdot H^c} + d$		
	where H expressed in oersteds, and: $a=1.00E-02$, $b=1.34E-08$, $c=1.55$, $d=0.00$		
	H_{DC}	200 Oe	
	Percent Initial Perm(nom.)	99.5%	
Coating/Plig	Coating Type:	Parylene C	
	Voltage Breakdown (min.)	500 Vrms, 60Hz	
	Limit	3 mA, 5 s	
	Package Quantity	250,000 Pcs/Box	

Winding Table	Wire Size	AWG	30	32	34	36	38	40	42	44	#N/A	#N/A	#N/A
		mm	0.250	0.200	0.160	0.125	0.100	0.080	0.063	0.050	#N/A	#N/A	#N/A
	Single Layer	Turns	11	14	18	23	30	38	47	60	#N/A	#N/A	#N/A
		Rdc(Ω)	20.0 m	40.5 m	82.8 m	168.3 m	349.0 m	703.1 m	1.4	2.8	#N/A	#N/A	#N/A
Full Winding	Turns	11	16	25	39	60	93	145	224	#N/A	#N/A	#N/A	
	Rdc(Ω)	20.0 m	46.3 m	115.0 m	285.3 m	698.0 m	1.7	4.3	10.5	#N/A	#N/A	#N/A	

