



**Part Number:** T7-1

Revision 20190524 - Generated 2019-May-30



<b>OD</b>	(nom. - bare core) (max. - after coating)	1.78 mm 1.91 mm	0.070 in 0.075 in										
<b>ID</b>	(nom. - bare core) (min. - after coating)	0.89 mm 0.76 mm	0.035 in 0.030 in										
<b>Ht</b>	(nom. - bare core) (max. - after coating)	0.76 mm 0.89 mm	0.030 in 0.035 in										
<b>Mass</b>	(approximate)	0.01 grams											
<b>Magnetic Dimensions</b>	A <sub>e</sub> - Eff. Mag. Cross Section	0.00350 cm <sup>2</sup>											
	L <sub>e</sub> - Eff. Mag. Path Length	0.420 cm											
	V <sub>e</sub> - Eff. Core Volume	0.00150											
	WA - Min. Eff. Window Area	0.00456 cm <sup>2</sup>											
	sa - Surface Area	0.135 cm <sup>2</sup>											
<b>Inductance</b>	μ <sub>i</sub> (reference)	20											
	A <sub>L</sub> value (nominal)	3.5 nH/N <sup>2</sup>											
	Test Winding	N=10, #36 AWG											
	Frequency	1 MHz											
	Voltage on Agilent 4284A	0.016 V											
<b>Core Loss</b>	A <sub>L</sub> tolerance	±10%											
	Core Loss(mW/cm <sup>3</sup> )=	$\frac{f}{\frac{a}{B_{pk}^3} + \frac{b}{B_{pk}^{2.3}} + \frac{c}{B_{pk}^{1.65}}} + d \cdot B_{pk}^2 \cdot f^2$											
	where B <sub>pk</sub> expressed in gauss, f expressed in hertz, and:	a=1.90E+09, b=2.00E+08, c=9.00E+05, d=4.30E-15											
	B <sub>pk</sub>	140 G											
	frequency	100 kHz											
<b>DC Saturation</b>	Core Loss (nominal)	31 mW/cm <sup>3</sup>											
	Core Loss (maximum)	36 mW/cm <sup>3</sup>											
	%μ <sub>i</sub> =	$\frac{1}{a + b \cdot H^c} + d$											
	where H expressed in oersteds, and:	a=1.00E-02, b=1.14E-06, c=1.43, d=0.00											
	H <sub>DC</sub>	200 Oe											
<b>Coating/Pkg</b>	Percent Initial Perm(nom.)	82.2%											
	Percent Initial Perm(min.)	78.0%											
	Coating Type:	Parylene C											
	Voltage Breakdown (min.)	500 Vrms, 60Hz											
<b>Winding Table</b>	Limit	3 mA, 5 s											
	Package Quantity	250,000 Pcs/Box											
	<b>Wire Size</b>	AWG	36	38	40	42	44	#N/A	#N/A	#N/A	#N/A	#N/A	#N/A
		mm	0.125	0.100	0.080	0.063	0.050	#N/A	#N/A	#N/A	#N/A	#N/A	#N/A
	<b>Single Layer</b>	Turns	11	14	18	24	30	#N/A	#N/A	#N/A	#N/A	#N/A	#N/A
Rdc(Ω)		49.5 m	100.1 m	204.7 m	434.1 m	863.0 m	#N/A	#N/A	#N/A	#N/A	#N/A	#N/A	
<b>Full Winding</b>	Turns	11	17	26	40	62	#N/A	#N/A	#N/A	#N/A	#N/A	#N/A	
	Rdc(Ω)	49.5 m	121.6 m	295.7 m	723.5 m	1.8	#N/A	#N/A	#N/A	#N/A	#N/A	#N/A	

