



Mix: -14

Revision 20190524 - Generated 2019-May-24

μi(reference)	14
Typical AL tolerance	± 10%
Color Code	Black/Red
Density	5.2 g/cm ³
Bsat	15.2kG
Core Loss (100kHz, 140g)	18 mW/cm ³ (nom) 21 mW/cm ³ (max)
%Perm at DC Bias (200 Oe)	91.8% (nom) 89.6% (min)

