



<b>Mix:</b>	<b>-35</b>
-------------	------------

Revision 20190524 - Generated 2019-May-24

$\mu_i$ (reference)	33
Typical AL tolerance	$\pm 10\%$
Color Code	Yellow/Gray
Density	6.3 g/cm <sup>3</sup>
B <sub>sat</sub>	17.3kG
Core Loss (100kHz, 140g)	119 mW/cm <sup>3</sup> (nom) 137 mW/cm <sup>3</sup> (max)
%Perm at DC Bias (100 Oe)	73.3% (nom) 68.0% (min)

