



Mix:	-52
-------------	------------

Revision 20190717 - Generated 2019-Jul-17

μ (reference)	75
Typical AL tolerance	$\pm 10\%$
Color Code	Green/Blue
Density	7.0 g/cm ³
Bsat	18.5kG
Core Loss (100kHz, 140g)	58 mW/cm ³ (nom) 67 mW/cm ³ (max)
%Perm at DC Bias (50 Oe)	61.6% (nom) 53.4% (min)

